



ONE-COMPONENT POLYURETHANE ADHESIVE SEALANT

EAN code: 5907588404310 item no.: 00700331 white
EAN code: 5907588400299 item no.: 0070032 grey
EAN code: 5907588404303 item no.: 0070033 black



+ PROPERTIES

The polyurethane adhesive sealant is a one-component compound that forms a strong seal with the participation of the moisture contained in the air. The creamy, compact texture does not drip off and does not form shrinkage. It has good adhesion to raw and painted sheet metal, aluminum, glass, wood, plastic and concrete. It is resistant to oils, salt, water and weather. Thanks to its elasticity combined with high strength, it acts as an anti-vibration and reinforcement mass for the body structure. It is used to connect and seal welds between sheets at locations such as welds, spot welds for overlapping, etc. It is also used to connect plastic, glass and metal elements as well as to seal body parts such as headlight brackets, roof windows, etc. Does not contain silicone.

• COLOUR

○ white

● grey

● black


⤿ METHOD OF USE

Packaging dedicated to tube squeezers.

↓ APPLICATION



Thoroughly clean and degrease the surface



Apply with a BOLL squeezer



Hardening time: 3h w 20°C



It can be varnished with all varnish systems



PHYSICAL PROPERTIES

solid content:	> 94%
density at 20°C:	approx. 1,17 g/cm ³
tensile strength:	approx. 2 N/mm ²
shear strength:	approx. 1 N/mm ²
tearing strength:	13 N/mm
time of formation of the outer layer at 23°C and 50% relative humidity:	approx. 60 min
cure time at 23°C and 50% relative humidity:	4 mm in 24 hours
Shore A hardness:	approx. 50
modulus at break:	0,6 MPa
elongation to break:	> 600 %
resistance to diluted acids:	medium
UV resistance:	good
resistance to water and salt:	excellent
heat resistance:	-40°C to +90°C



CZYSZCZENIE SPRZĘTU

Wash with a solvent for nitrocellulose (Nitro) or acrylic products.



STORAGE CONDITIONS



Protect the product from excessive heat and cold. Avoid direct exposure to sunlight. Store in a dry place.



SHELF LIFE

Placed on the package.



SAFETY

See Safety Data Sheet



OTHER INFORMATION

All technical data are approximate values. We advise you to test the material to ensure suitability for your specific application. The producer reserves the right to improve the product and change the technical conditions with the possibility of making changes inside the specification.