



Fisa Tehnica



Icopal VA Top 40 SBS

STN EN 13707

DESCRIERE

Membrana din bitum modificat pentru lucrari de hidroizolatii la : constructii noi, renovari si elemente de constructie aflate in subsoluri.

Tipurile de aplicatii: strat superior in sisteme hidroizolante multistrat ale teraselor.

Metoda de aplicare: prin termosudare cu flacara.

COMPOZITIE

Fata superioara	Ardezie
Suprafata de suprapunere longitudinala	Film
Compozitie bitum	SBS (Styrene-Butadiene-Styrene) bitum elastomeric
Armatura	Fibra de sticla
Fata inferioara	Film

CARACTERISTICI DIMENSIONALE

Greutate	kg/m ²	4,0 ± 0,2
Grosime, inf.	mm	3,0
Latimea marginii longitudinale de suprapunere	mm	100
Lungimea si latimea rolei	m	10 x 1

PERFORMANTE

Caracteristici	Metode de test / Norma referinta	Unitati	Valori medii
Rezistenta la intindere longitudinal/transversal	EN 12311-1	N/5cm	550/320 (±20%)
Elongatia longitudinal/transversal	EN 12311-1	%	3,0 /3,0 (±20%)
Flexibilitatea la temperaturi scazute	EN 1109	°C	- 10
Stabilitatea dimensionala la temperaturi inalte	EN 1110	°C	+ 85
Impermeabilitatea la 100 kPa/24h	EN 1928	—	conforma
Reactia la foc	EN 13501-1	--	clasa F

Ambalare

Role/palet	Bucati	20
m ² /palet	m ²	200
Greutate/m ²	kg	4,0
Greutate/rola	kg	40

Nota marcaj CE:

Certificat de control al productiei in fabrica nr.: 1020 – CPD - 010029639