

## Anycubic High Clear Resin Parameters

UV wavelength	365-405nm
Density	1.05-1.25g/cm <sup>3</sup>
Viscosity	266 cP·mPa·s
Yellowing resisting time	>30 Minutes
Flexural modulus	>798 MPa
Resin wash	Alcohol
Elongation at break	14.6%
Molding shrinkage	3.72-4.24%
Flexural strength	30.3 MPa
Hardness	78D
Tensile strength	28.1 MPa
Conservation period	12 Months