

Anycubic High Speed Resin Parameters

UV wavelength	365-405nm
Density	1.15g/cm³
Viscosity	55-65 cP·mPas
Hardness	90-93D
Tensile strength	45-60 MPa
Elongation at break	6-9%
Molding shrinkage	5.1-6.2%
Flexural strength	60-85 MPa
Flexural modulus	1800-3000 MPa
Conservation period	12 Months