

Anycubic Water-Wash Resin + Parameters

UV wavelength	365-405nm
Density	1.15-1.20g/cm ³
Viscosity	150-250 MPa·s (25°C)
Flexural modulus	>1500-1600 MPa
Heat deflection temp	>60-65°C
IZOD Impact Strength	>50-60J/m
Elongation at break	8-15%
Tensile modulus of elasticity	1600-1800 MPa
Flexural strength	30-45 MPa
Hardness	80Shore D
Tensile strength	50-60 MPa
Conservation period	1.5 Year