

## **Anycubic Standard UV Resin Parameters**

UV wavelength	365-405nm
Density	1.13g/cm <sup>3</sup>
Viscosity	200-230 cP·mPa·s
Hardness	84-86 HS
Tensile strength	40-50 MPa
Elongation at break	12-16%
Molding shrinkage	4.5-5.5%
Flexural strength	50-60 MPa
Flexural modulus	1400-1600 MPa
Conservation period	18 months