

Rasina Anycubic ABS Like Resin V2

Technical Data Sheet

UV wavelength	365-405nm	Elongation at break	30-40%
Density	1.1-1.2 g/cm ³	Molding shrinkage	4.3-5.6%
Viscosity	180-200 cP·mPa·s	Flexural strength	40-50MPa
Hardness	80-85D	Flexural modulus	1000-1200 MPa
Tensile strength	35-45 MPa	Heat deflection temp	60-65°C
Bottom exposure time	20-40s	Resin wash	Water/Alcohol
Normal exposure time	1.5-3s (color screen 8s)	Shelf life	1.5 Year