

Technical Data Sheet

PET-G PROGRAFEN GRAPHENE LIGHT

PET-G PROGRAFEN GRAPHENE: a thermoplastic polymer. PET-G PROGRAFEN GRAPHENE is a black general purpose 3D printing extrusion grade polymer. This is a high molecular weight polymer that processes easily on conventional extrusion equipment. Extruded roll stock is readily thermoformable. See table for typical properties.

Applications

Potential applications for PET-G PROGRAFEN GRAPHENE LIGHT include:

- Prototype 3D models
- Tooling
- Construction elements
- Every-day-use items

Processing Information

PET-G PROGRAFEN GRAPHENE LIGHT is easily processed on FDM/FFF 3D printers. The material is stable in the filament state, if it is being stored in a dry environment

Process Details

Preparation for printing

PET-G Graphene Light is graphene enhanced PET-G filament, before printing following steps must be taken:

1. **Load filament into extruder head:** Is very important to heat up extruder before printing (optimal extruder temperature are 210-260 °C). When extruder reach set temperature insert filament into the way approved by 3D Printer manufacturer.
2. **Level up printing table and turn up it's heating** (optimal printing table temperatures for PET-G are 60-70 °C).
3. **Upload previously prepared 3D model into 3D Printer controller.**
4. **Printing process can be started.**

Typical Material & Application Properties ⁽¹⁾

Physical Properties	PET-G PROGRAFEN GRAPHENE LIGHT	Method
Specific Gravity	1.29	D792
MFR, g/10 min (230°C, 2.16kg)	18.2	ISO 1133
Color	Black	
Mechanical Properties		
Tensile Strength, MPa	53	ISO 527
Tensile Modulus, GPa	2.4	ISO 527
Elongation at break, %	4.57	ISO 527
Impact strength, kJ/m ²	3.73	ISO 179

(1) Typical properties; not to be construed as specifications.

Processing Temperature Profile ⁽¹⁾

Extruder Head Temperature	210-245°C
Printing table Temperature	60-70°C
Post-treatment	Painting, smoothing

(1) These are starting points and may need to be optimized.

Storage

In order to maintain the highest possible quality of the printout, care should be taken to properly protect the filament against moisture. The filament should be stored in a cool, dry and shaded place. In case of problems with too high humidity, drying agents can be used, which should be placed in the filament packaging. The original packaging maintains optimal humidity and temperature of the filament.

Safety and Handling Considerations

Safety Data Sheets (SDS) for PET-G PROGRAFEN GRAPHENE LIGHT are available at <https://prografen.com>. SDS's are provided to help customers satisfy their own handling, safety, and disposal needs, and those that may be required by locally applicable health and safety regulations. SDS's are updated regularly; therefore, please request and review the most current SDS's before handling or using any product.

Hazards and Handling Precautions

PET-G polymers have a very low degree of toxicity and, under normal conditions of use, should pose no unusual problems from incidental ingestion or eye and skin contact. However, caution is advised when handling, storing, using, or disposing of these resins, and good housekeeping and controlling of dusts are necessary for safe handling of product. No other precautions other than clean, body-covering clothing should be needed for handling PET-G polymers. Use gloves with insulation for thermal protection when exposure to the melt is localized. Workers should be protected from the possibility of contact with molten resin during fabrication.

Handling and fabrication of resins can result in the generation of vapors and dusts that may cause irritation to eyes and the upper respiratory tract. In dusty atmospheres, use an approved dust respirator.

Good general ventilation of the polymer processing area is recommended. At temperatures exceeding the polymer melt temperature (typically 175°C), polymer can release fumes, which may contain fragments of the polymer, creating a potential to irritate eyes and mucous membranes. Good general ventilation should be sufficient for most conditions. Local exhaust ventilation is recommended for melt operations. Use safety glasses (or goggles) to prevent exposure to particles, which could cause mechanical injury to the eye. If vapor exposure causes eye discomfort, improve localized fume exhausting methods or use a full-face respirator.

Disposal

DO NOT DUMP INTO ANY SEWERS, ON THE GROUND, OR INTO ANY BODY OF WATER. For unused or uncontaminated material, the preferred option is to recycle into the process otherwise, send to an incinerator or other thermal destruction device. For used or contaminated material, the disposal options remain the same, although additional evaluation is required. Disposal must be in compliance with Federal, State/Provincial, and local laws and regulations.

Environmental Concerns

Due to its chemical composition, PET-G does not pose a threat to the environment. Nevertheless, plastics should be disposed of in appropriately labeled containers.

Contact:

Spectrum Group Sp. z o.o.
Parkowa 85
05-806 Pecice, Poland
office@spectrumfilaments.com



Disclaimer:

The technical information, recommendations and other statements contained in this document are based upon tests or experience that Spectrum Group Sp z o.o. believes are reliable, but the accuracy or completeness of such information is not guaranteed. Many factors beyond Spectrum Group Sp z o.o. control can affect the use and performance of a Spectrum Group Sp z o.o. product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge or control, it is essential that the user evaluate the Spectrum Group Sp z o.o. product to determine whether it is fit for a particular purpose and suitable for the user's method of application. In addition, because use conditions are outside of Spectrum Group Sp z o.o. control and applicable laws may differ from one location to another and may change with time, Customer is solely responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace, use and disposal practices are in compliance with applicable laws and regulations. Spectrum Group Sp z o.o. assumes no obligation or liability for the information in this document. Spectrum Group Sp z o.o. makes no warranty, express or implied, regarding the information contained herein or its products, including but not limited to any warranty as to accuracy or completeness of information, or any implied warranty of merchantability or fitness for a particular purpose. No information in this publication can be considered a suggestion to infringe patents.