

Colour:	
Production origin:	
Content:	50,00 g
Base:	Methyl methacrylate
Viscosity:	thixotropic
Shelf life:	12 months
Temperature resistance:	-50 °C to +150 °C
Hardness:	74 Shore D
Gap filling capacity:	10 mm
Pot life:	4-6 min
Tensile strength:	22-24 MPa (N/mm², ASTM D 638)
Functional strength:	1-3 h
Fixing time:	15 min