

Colour:	
Production origin:	
Content:	360,00 g
Base:	polyurethane
Viscosity:	pasty
Density:	1.18 g/ml
Working temperature:	+5 °C to +30 °C
Stability:	< 2 mm (ISO 7390)
Shrinkage:	10 % (ISO 10563)
Skin formation time:	~ 60 min
Curing speed:	4 mm/24 h (23 °C, 50 % relative humidity)
Temperature resistance:	-40 °C to +90 °C
Hardness:	50 Shore A (DIN 53505)
Module 100 %:	0.6 MPa (N/mm²)
Elongation at break:	> 400 %
Tensile strength:	2.1 MPa (N/mm²)