

Colour:	
Production origin:	
Content:	25,00 g
Base:	Methyl methacrylate
Viscosity:	150,000-200,000 mPa·s at +20 °C (Brookfield)
Density:	~ 0.97 g/ml
Shelf life:	12 months
Shrinkage:	5 %
Temperature resistance:	-55 °C to +120 °C
Hardness:	75 Shore D
Gap filling capacity:	1-10 mm
Pot life:	5-7 min
Fixing time:	10-12 min