


Colour: 

Production origin: 

Content: 50,00 g

Base: Methyl methacrylate

Viscosity: 150,000-200,000 mPa·s at +20 °C (Brookfield)

Density: ~ 0.97 g/ml

Shelf life: 12 months

Shrinkage: 5 %

Temperature resistance: -55 °C to +120 °C

Hardness: 75 Shore D

Gap filling capacity: 1-10 mm

Pot life: 5-7 min

Fixing time: 10-12 min