

Colour:



Production origin:



Content:

25,00 g

Base:

polyurethane based on HDI and polyols

Viscosity:

~ 55,000 mPa·s at +25 °C (Brookfield)

Working temperature:

+5 °C to +30 °C

Shelf life:

12 months

Shrinkage:

< 1 %

Curing speed:

24 h

Temperature resistance:

-40 °C to +120 °C (short term to +140 °C)

Hardness:

65 Shore D

Elongation at break:

~ 2-3 %

Gap filling capacity:

~ 5 mm

Pot life:

~ 90 s

Tensile strength:

> 30 N/mm² (DIN 53504)

Processing time:

~ 30 min

Tackiness when dry:

~ 3 min