


# CONIFLOOR COLORQUARZ LE

(Colorquarz Epoxy System Low Emission)

Hard, decorative, low emission, coloured quartz floor coating based on epoxy resin and Polyaspartic resin, statically and high mechanical strength, anti-slip R9 - R12 for dry and wet areas, for indoor use



- 1 Primer optional
- 2 Scratch primer / Levelling
- 3 Wear coat with Colorquarz
- 4 Top coat transparent

## System design and consumption

	LAYER	PRODUCT	CONSUMPTION (kg/m <sup>2</sup> )	QS / FILLER (kg/m <sup>2</sup> )	APPLICATION
1	Primer / blocking primer (optional) on strongly absorbent u. porous substrates, or as blocking primer	CONIFLOOR EP 116 LE or CONIFLOOR EP 112 LE	0.3 – 0.5 as blocking primer min. 0.5 – 0.6 (film forming)	QS 03/08 0.8 – 1.0 no QS scattering as blocking primer	Squeegee / roller / brush Sand broadcasting, not in excess, as <b>blocking primer no sand scattering!</b>
2.1	Scratch primer / levelling	CONIFLOOR EP 116 LE filled with QS 01/03 filled with QS 03/08 or QS 06/12  QS 03/08 scattering in excess	0.8 (resin) 0.6 (QS 01/03) 0.2 (QS 03/08) or 0.2 (QS 06/12)  03/08 in excess	QS 01/03 for filling QS 03/08 for filling or QS 06/12 for filling  Scattering of QS 03/08 ≥ 3.0 – 4.0	Trowel / smoothing rake, scratched on biggest grain  Scattering in excess, after curing sweeping not integrated QS and grinding and vacuum cleaning
3	Decorative wear coat with coloured quartz sand	CONIFLOOR EP 116 LE filled with QS 01/03 filled with QS 03/08  Colour quartz sand 04/08 scattered in excess	0.8 (resin) 0.6 (QS 01/03) 0.2 (QS 03/08)  Colour quartz sand 04/08 in excess	QS 01/03 for filling QS 03/08 for filling  Scattering colour quartz sand 04/08 in excess	Trowel / smoothing rake, scratched on biggest grain  Scattering in excess, after curing sweeping not integrated QS and grinding and vacuum cleaning
4	Top coat transparent, glossy, UV- and colour stable, fast curing	CONIFLOOR PAS 585 LE in 1* or 2** layers	0.5 – 0.9*  0.4 – 0.5** + 0.15 – 0.3**	none	Trowel / Soft or hard squeegee or spatula  Re-rolling immediately within 3 minutes!
5	Sealing lacquer (PU) transparent, matt (optional)	CONIFLOOR 520 W	0.12 – 0.15	none	Roller
	System layer thickness	ca. 2.0 – 4.5 mm			
	Subsoil	Surfaces must be clean, stable, and free of cracks and voids. In general, substrates must be provided in accordance with the applicable regulations. (See also "General processing guidelines for CONICA coatings, CONICA seals and CONICA parking deck coating systems"). Adhesive tensile strength ≥ 1.5 N / mm <sup>2</sup> , max. Residual moisture ≤ 4% -CM, on cementitious substrates. Special precautions must be taken in the event of higher residual moisture levels and moisture by rising water. Preparation of the surface e.g. by grinding (diamond) or shot blasting (Blastrac) with subsequent sweeping and vacuuming is mandatory. The above-mentioned consumption values have been determined in the laboratory under practical conditions to achieve the technical properties. In the case of existing on-site conditions and conditions such as temperature, surface roughness etc., the consumption values may deviate from the stated values. In case of doubt, we recommend creating sample areas on site.			
	Note	For other substrates, which are not mentioned here or special requirements, special primers must be used if necessary, please ask our technical service. Detailed processing instructions can be found in the respective product data sheets or are available on request..			

## High Performance Flooring

## Areas of application

- Production halls with wet conditions,
- Productions in food & beverage
- Kitchens and catering (warm water up to 60°C permanent)
- Public buildings (entrance halls, changing rooms, corridors)
- Workshops, metal working areas e.g. watch industry
- Pharmaceutical production

## System properties

- **Low yellowing or non-yellowing top coats**
- **Wide colour range** with coloured quartz sand
- **Low emission**
- **Anti-slip surfaces** R9 – R12
- **Trafficable with fork lift**, pallet trucks, cars and similar
- Hard, suitable for high mechanical load
- **Hygienic**, seamless and joint less surfaces,
- **Seamless connection to vertical surfaces**
- Fire behaviour class **B<sub>fl</sub>-s1**



## Technical data (internal / external approvals)

PROPERTIES	STANDARD	VALUES
Shore-Hardness	DIN ISO 868	67 D after 28 d
Flexural strength	EN 196 / ASTM C109	ca. 42 N/mm <sup>2</sup>
Compressive strength	EN 196 / ASTM C109	ca. 65.5 N/mm <sup>2</sup>
Chemical resistance	EN ISO 2812-1	DiBT test liquids 10, 11,12 and others
Impact strength	DIN EN 13813	≥ 4 Nm (IR4)
Abrasion resistance (Taber)	ISO 9352, ASTM D 1044	≤ 62 mg (incl. top coat)
Abrasion resistance (BCA)	DIN EN 13813	AR ≤ 1,0
Slip resistance	DGUV Regel 108-003 / DIN 51130	Class R9 / R10 / R11-V4 / R12-V6
Adhesive strength	DIN ISO 4624	≥ 1.5 N/mm <sup>2</sup> (Depends on substrate)
Fire classification	EN 13501-1	B <sub>fl</sub> -s1

**CONICA AG**  
 Industriestrasse 26  
 8207 Schaffhausen/ Swiss  
 Tel. +41 (0)52 644 36 00  
 Fax +41 (0)52 644 36 99  
[info@conica.com](mailto:info@conica.com)  
[www.conica.com](http://www.conica.com)

The content of this information sheet is non-binding. With regard to the variety of surfaces and object conditions on the one hand, and on the other hand due to the fact that the application and processing of this product are beyond our control, the buyer and / or user is not released from the obligation to its own responsibility, to check and ensure, that this product is suitable for the intended use. Our verbal, written advice and tests is non-binding.

*With the publication of this issue, all previous information on this system is no longer up to date. Since the data sheets are updated regularly, it is the responsibility of the user to have the current version available. Registered users can download current data sheets from our homepage at any time. We would be happy to send them to you on request.*