

# CONIFLOOR 465

**Two-part PUR coating, pigmented, fast curing, low emission, total solid, self-levelling, tough hard**

## Product description

CONIFLOOR 465 is a two component, solvent free and low emission, **fast curing**, self-levelling, pigmented, **tough hard PUR coating**.

## Fields of application

CONIFLOOR 465 is used as a **statically crack bridging** self-levelling and fast curing coating or as broadcasted wear coat on mineral, primed (with CONIFLOOR EP 110, EP 118 or CONIFLOOR 160) substrates for indoor floorings with medium to heavy mechanical stress.

On bituminous substrates (cast asphalt with sufficient rigidity and hardness), CONIFLOOR 465 can be used as scratch primer in this case.

## Properties

CONIFLOOR 465 exhibits high mechanical properties and is easy to apply. Due to its hard and tough properties the coating CONIFLOOR 465 is still slightly elastic and

therefore is able to bridge deformations (e.g. occurring static cracks) in the sub-base.

CONIFLOOR 465 is easy to clean and resistant to water, sea and wastewater, a variety of alkaline substances, diluted acids, brine, mineral oils, lubricants and fuels.

The yellowing, which occurs when CONIFLOOR 465 is exposed to UV light, does not affect its mechanical properties. To avoid the yellowing the coating can be sealed with CONIFLOOR 520 CW or CONIFLOOR PAS 585 C LE which at the same time increases the resistance against scratches.

CONIFLOOR 465 is used in our indoor flooring systems

- CONIFLOOR IPS rapid
- CONIFLOOR IPS rapid SR

and others.

## Technical Data

<b>Mixing ratio</b>	in parts by weight			100 : 48
<b>Density</b>	mix,	at 23 °C	g/cm <sup>3</sup>	1.05
<b>Viscosity</b>	mix,	at 23 °C	mPas	1700
<b>Processing time</b>	at 10 °C		min.	35
	at 20 °C		min.	25
	at 30 °C		min	15
<b>Re-coating interval / ready for foot traffic</b>	at 10 °C		min. h	8
	at 20 °C		min. h	4
	at 30 °C		min. h	3
<b>Substrate and application temperature</b>	minimum		°C	10
	maximum		°C	30
<b>Permissible relative humidity</b>	maximum		%	75
<b>Ready for</b> <b>mech. stress</b> <b>light mech. stress</b> <b>chemical stress</b>	at 10 °C		d	2
	at 20 °C		d	1
	at 30 °C		d	1
<b>Elongation</b>	after 7d /23°C		%	≥ 40
<b>Tensile strength</b>	after 7d /23°C		N/mm <sup>2</sup>	≥ 15
<b>abrasion after Taber CS10 / 1000g / 1000 cycles</b>	Average abrasion		mg	28.0
<b>Shore D hardness</b>	after 28 d			55
<i>Above figures are guide values and should not be used as a base for specifications!</i>				

## Application method

Please also [note](#) the [information in our general processing guidelines](#).

CONIFLOOR 465 is supplied in the correct proportions of component A (resin) and component B (hardener). Before mixing, the A component must be stirred up by machine, then the B component is poured into the container of the A component and ensure that the pail containing component B is [emptied](#) completely.

To achieve a homogenous mix, thoroughly mix with a slowly rotating mixing device at about 300 rev/min. Ensure that the mixing device reaches side and bottom areas of the mixing vessel. The [mixing](#) process takes [at least 3 minutes](#) and should be performed until the blend is [homogenous](#) and streak free. [Pour](#) the mix into another [clean](#) pail and mix it again for 1 additional minute.

The [temperature](#) of the components should be between 15-25 °C.

CONIFLOOR 465 can then be applied directly to the pre-treated substrate or – when used as thick self-levelling coating of at least 2 mm thickness – the coating can be filled while constantly stirring with up to 30% with quartz sand with a grain size of 0.1-0.3 mm.

CONIFLOOR 465 is applied using a squeegee, scraper or a notched trowel. The teeth size of the tool needs to be adjusted to the calculated consumption per 1m<sup>2</sup>

Cross-wise [spike rolling](#) after application is necessary to [de-aerate](#) the coating.

The ambient and substrate temperature influences working life and curing time of CONIFLOOR 465. At low temperatures, the chemical reactions are slowed down; this lengthens the pot life, re-coating interval and open time. High temperature and humidity accelerate chemical reactions, so the contrary is true.

To fully cure the material, the substrate and working temperature must not fall below the minimum.

After application, the material should be protected from direct contact with water for approx. 4 hours (at 15 °C). Within this period, contact with water can cause foaming on the surface of the coating.

The relative [humidity](#) level may not exceed [70%](#).

## Consumption

The consumption rate of CONIFLOOR 465 for a layer of at least 1.5 mm is 2.3 kg/m<sup>2</sup>.

The [maximum](#) thickness of this coating layer should not exceed 2.5 mm.

In case of layers, ≥ 2 mm the coating can be filled with oven dried quartz sand with a grain size of 0.1-0.3 mm. The mixing ratio coating: quartz sand can be up to 1:0.3 by weight (30%). The share of binder then is approximately 2.6 kg/m<sup>2</sup>.

Depending on the on the surface roughness of the cast asphalt the consumption of CONIFLOOR 465 used as base scratch coat is approximately 0.8-1.2 kg/m<sup>2</sup>.

## Cleaning agent

Re-usable tools should be cleaned carefully with CLEANER 40, CLEANER 45 or other suitable solvents (e.g., butyl acetate).

Never use water or alcoholic solvents as cleaners!

## Substrate condition

Cement bound substrates to be coated must be firm, dry, load bearing and free of loose and brittle particles and substances, which impair adhesion such as oil, grease, rubber skid marks, paint or other contaminants.

A pre-treatment of the substrate by grit or shot blasting, high-pressure water jetting, grinding or scabbing including the necessary post-treatment is mandatory.

After the pre-treatment, the bond strength of the concrete must be at least 1.5N/mm<sup>2</sup>. The [moisture level](#) must not exceed [4 %](#).

The [temperature](#) of the substrate must be at least [3°C](#) above the current dew point temperature.

The sub base must contain a moisture barrier (damp proof membrane D.P.M.).

CONIFLOOR 465 is applied on the pre-treated and with CONIFLOOR EP 110, EP 118 or CONIFLOOR 160 primed sub-base.

## Notice for bituminous sub-bases:

CONIFLOOR 465 is used as a primer and applied as a thin layer directly on bituminous sub-bases (cast asphalt used indoors with sufficient hardness).

Then apply CONIFLOOR 465 as self-levelling coating.

When preparing the sub-base by grit blasting with the necessary post-treatment (dust free!) special attention needs to be paid to the grains in the cast asphalt. At least 70 % of the grains need to be open and free of asphalt to allow sufficient adhesion.

If needed the quality of the sub-base needs to be tested carefully – contaminations in the cast asphalt have to be avoided.

After the pre-treatment, the bond strength of the concrete must be at least 1.5N/mm<sup>2</sup>.

As for the rest the sections of the requirements concerning substrates to be coated shown in the according guidelines apply.

## Pack size

CONIFLOOR 465 is supplied in 25 kg (metal) working packs. Components A and B are supplied in the correct proportions and delivered separately.

## Colours

Standard colours after approx. RAL or on request

**Note:** Please note that **aromatic polyurethane resins turn yellow due to UV light**. This also applies to indoor applications. As we generally recommend an additional UV and colour-stable, pigmented aliphatic polyurethane resin sealing lacquer on these products, **no colour matching is performed**.

The colour meets colour standards such as RAL or NCS and others with a colour deviation of  $\Delta E \leq 2$  (otherwise  $\Delta E \leq 1$ ).

Please also note our supplementary information on colours and surfaces.

If necessary, and especially with very light shades, it may be necessary to seal twice in white shades up to three times. .

If you have any questions, please contact the technical service of CONICA AG.

### Storage

Store in unopened pails under dry conditions at a temperature range of 5-25 °C.

Do not expose to direct sunlight.

Before use, please see "best before" date on the pail / drum.

### Safety precautions

CONIFLOOR 465 is non-hazardous in its cured condition.

For protective measures, transport regulations and waste management please refer to the Material Safety Data Sheet of the product.

### VOC contents

CONIFLOOR 465 meets the requirements of the EC directive 2004/42/EC.

The limit value for products ready for use (product type according to table IIA j Type sb) is:

Level II (from 2010) <500 g/l VOC.

When ready to use, this product contains less than 500 g/l VOC.



### CE and UKCA marking:

See Declaration of Performance

CONICA AG  
Industriestrasse 26  
8207 Schaffhausen  
Suisse

Tel.: + 41 52 644 3600  
Fax: + 41 52 644 3699  
[info@conica.com](mailto:info@conica.com)  
[www.conica.com](http://www.conica.com)

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given, or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the professional competence involved in the application of the product are beyond our control.

*As all CONICA data sheets are updated on a regular basis, it is user's responsibility to obtain the most recent issue. Registered users can obtain the actual data sheets from our webpage. Hard copies are available upon request.*