

CONIFLOOR 520 CW ab

Two-part PUR sealing lacquer, tested accord. ISO 22196:2011, pigmented, water based, low emission, UV- and colour stable, with silk-mat finish for hard CONICA EP and PUR coatings

Product description

CONIFLOOR 520 CW ab is a water based solvent free, [low emission and pigmented UV- and colour stable](#) two-component silk-mat finished [PUR sealing lacquer](#) of low viscosity with [tested](#) surface accord. ISO 22196:2011 and used on tough hard and hard PUR and EP coatings.

Fields of application

CONIFLOOR 520 CW ab is used as UV resistant, pigmented sealing lacquer on [hard](#) EP and PUR coatings. Due to the hygienic properties, the area of application is especially in [healthcare and nursing facilities](#), but other areas that are subject to higher hygiene requirements can be equipped with CONIFLOOR 520 CW ab.

Properties

CONIFLOOR 520 CW ab exhibits good adhesion to non-porous substrates and is used as pigmented top sealer which is easy to apply, good to clean and features a good scratch-resistance, furthermore, the [risk of germs spreading through the floor covering is reduced](#).

Fully cured, CONIFLOOR 520 CW ab exhibits excellent mechanical properties and chemical resistance.

CONIFLOOR 520 CW ab is used in the systems

- CONIFLOOR IPS
- CONIFLOOR IPS H
- CONIFLOOR IPS rapid
- CONIFLOOR IES

and other systems. .

Technical Data

Mixing ratio	in parts by weight		100:25
Density	mix, at 23 °C	g/cm ³	1.16
Viscosity	at 20 °C	mPas	800 - 1100
Pot life (10kg mixture)	at 20 °C	min	ca. 45
Re-coating interval	min., at 23 °C, 50 % rel. humidity	h	18 - 24
	max. at 23 °C, 50 % rel. humidity	h	30
Ready for foot traffic	at 20 °C, 50 % relative humidity	h	18 - 24
Fully cured - ready for exposure to chemicals	at 23 °C, 50 % relative humidity	d	7
Substrate and application temperature	at least	°C	10
	maximum	°C	30
Permissible relative humidity	maximum	%	75
Taber	ISO 5470-1 (500g//CS10)	mg	14,8
Scratch resistance	DIN 55656	N	15
<i>Above figures are guide values and should not be used as a base for specifications!</i>			

Application method

Please also note the [information in our general processing guidelines](#).

The [temperature](#) of both components should be between 15 - 25 °C.

CONIFLOOR 520 CW ab is supplied in the correct proportions of component A (resin) and component B (hardener). Before mixing, the A component must be stirred up by machine, then the B component is poured into the container of the A component.

Care must be taken to ensure that the B component leaks completely, while carefully scraping out the container of spatulas. First, the B component is poured into the container of the A component. Care must be taken to ensure that the B component leaks completely, while carefully scraping out the container of spatulas.

To achieve a homogenous mix, thoroughly mix with a slow rotating mixing device at about 300 rev/min.

Ensure that the mixing device reaches the side and bottom areas of the mixing vessel.

The [mixing](#) process takes approximately [2-3 minutes](#) and should be performed until the blend is [homogenous](#) and streak free.

[Do not](#) use the product out of the mixing pail. Pour the mix into another [clean](#) pail and mix it again for 2 more minutes. We recommend using a sieve or lacquer sieve when repotting in order to remove fine impurities, e.g., from the mixing equipment.

CONIFLOOR 520 CW ab is normally applied to the pre-treated substrate by [rolling](#) with a "Microtex" roller (Pile height: 10-12 mm). Roll out well, keep the overlap areas to a [minimum](#), and keep wet edge always wet with fresh material.

It is necessary to [re-roll](#) freshly applied material with a second clean paint roller [in one direction](#) in order to obtain a uniform surface with a minimum of overlap marks.

The connection line / overlapping times should [not exceed 4-5 minutes](#) in order to avoid the risk of roller marks.

The [areas of overlap](#) with the previous line should be kept as [small as possible](#), longer connection times and drafts should be avoided. [Switch off underfloor heating or reduce it](#) strongly before starting work.

The ambient, material, air circulations and substrate temperature influence the pot life and curing time of CONIFLOOR 520 CW ab. At low temperatures, chemical reactions are generally slowed down; this lengthens the pot life, re-coating interval and open time. At the same time, the viscosity increases which leads to a higher consumption. High temperature and humidity accelerate chemical reactions, so the contrary is true.

Important: Make sure that doors and windows are closed, to [avoid air circulation](#) during the application and curing. Airflow can [negatively](#) influence the optical properties by creating roller marks.

To fully cure the material, the substrate and working temperature must not fall below the minimum.

After application, the material have to be protected from direct contact with water. Within this period, water could cause swelling of the sealing lacquer or stain.

When using the CONIFLOOR 520 CW ab top coat, make sure that [no additional care products or cleaning agents are used that leave a film](#), as otherwise the specific hygienic properties are no longer present.

Consumption

The consumption of CONIFLOOR 520 CW ab is approximately between 0.12 – 0.14 kg/m²

Cleaning agent

Re-usable tools should be cleaned carefully with water.

Substrate condition

CONIFLOOR 520 CW ab is a hard top coat and is applied to our hard CONIFLOOR coatings CONIFLOOR 420 and CONIFLOOR 430 considering the expected mechanical strain to the system.

Substrates to be coated have to be firm, dry, load bearing and free of loose and brittle particles and substances, which impair adhesion such as oil, grease, rubber skid marks, paint, or other contaminants.

Sealing with CONIFLOOR 520 CW ab needs to be done latest [within 30 hours](#) (20°C) after latest application. Indicated re-coating intervals have to be kept.

The [temperature](#) of the substrate must be at least [3 °C](#) above the current dew point temperature.

Pack size

CONIFLOOR 520 CW ab is supplied in 10 kg working packs. A and B component are supplied separately in the correct proportions.

Colour

Standard colours available – further colours upon request

Care and Maintenance

In order to preserve the properties of synthetic resin floor coverings in the long term, we recommend regular maintenance. Please ask for our general care instructions. When using CONIFLOOR 520 CW ab, [make sure that no additional care products or cleaning agents are used that leave a film](#), otherwise the special hygienic properties are no longer given.

Storage

Store in original closed pails under dry conditions at a temperature range of 10 - 25 °C.

Important: Product is sensitive to [frost!](#)

Do not expose to direct sunlight.

Before use, please see "best before" date on the pail / drum.

Safety precautions

CONIFLOOR 520 CW ab is non-hazardous in its cured condition.

For protective measures, transport regulations and waste management please refer to the Material Safety Data Sheet of the product.

VOC contents

CONIFLOOR 520 CW ab meets the requirements of the EC directive 2004/42/EC.

The limit value for products ready for use (product type according to table IIA j Type wb) is:

Level II (from 2010) <140 g/l VOC.

When ready to use, this product contains less than 140 g/l VOC.



CE and UKCA marking:

See Declaration of Performance

CONICA AG
Industriestrasse 26
8207 Schaffhausen
Suisse

Tel.: + 41 52 644 3600
Fax: + 41 52 644 3699
info@conica.com
www.conica.com

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given, or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the professional competence involved in the application of the product are beyond our control.

As all CONICA data sheets are updated on a regular basis, it is user's responsibility to obtain the most recent issue. Registered users can obtain the actual data sheets from our webpage. Hard copies are available upon request.