

CONIFLOOR EP 112 N

Two-part EP resin primer, pre-filled, as primer and scratch coat, solvent free (total solid)

Product description

CONIFLOOR EP 112 N is a **prefilled**, low viscosity, two component epoxy resin-based primer, solvent free accord "Total Solid to the test methods Deutsche Bauchemie e.V.".

Fields of application

CONIFLOOR EP 112 N is designed for use as a primer, or a scratch coat, on mineral substrates indoors and outdoors such as concrete and cementitious screeds.

If necessary CONIFLOOR EP 112 N can additionally be filled with oven dried quartz sand size 0.1-0.3 or 0.1 – 0.4 mm. The **degree of filling depends on the temperature of ambient and material as well as the thickness of the layer** and can be filled up from 1:0.7 up to 1:1 part per weight.

Properties

CONIFLOOR EP 112 N is **pre-filled** in the factory, has a low viscosity and therefore shows high capillary activity.

The material has very good adhesion to substrates based on minerals and / or cement.

The yellowing which occurs when exposed to UV light does not impair its technical properties.

Fully cured, CONIFLOOR EP 112 N exhibits very good mechanical properties. It is resistant to water, sea, and waste water, as well a variety of alkalis, diluted acids, brine, mineral oils, lubricants, and fuels.

CONIFLOOR EP 112 N is content in the systems

- CONIPROOF PPC DL (OS 11a)
- CONIPROOF PPC SL (OS 11b)
- CONIPROOF PWC OS 10 (manual)
- CONIPROOF PEF (OS 8)

and other systems.

Technical Data

Mixing ratio	in parts by weight	A : B	100 : 27
Density	mix, at 23 °C	g/cm ³	1.50
Viscosity	mix, at 23 °C	mPas	ca. 1160
Working time (25 kg working packs)	at 10 °C	min.	45
	at 20 °C	min.	25
	at 30 °C	min.	10
Re-coating interval	at 20 °C	min.	h
		max.	h
Ready for foot traffic	at 10 °C	h	min. 24
	at 23 °C	h	min. 12
	at 30 °C	h	min. 7
Substrate and application temperature	minimum	°C	10
	maximum	°C	30
Max. permissible relative humidity		%	75
Shore D hardness	after 7 d		80
Tensile bond strength		N/mm ²	≥ 1,5
<i>Above figures are guide values and should not be used as a base for specifications!</i>			

Application method

Please also [note the information in our general processing guidelines](#).

CONIFLOOR EP 112 N is supplied in working packs, which contain the correct proportions of component A (resin) and component B (hardener).

Mixing

Before mixing, precondition both A and B components to a [temperature](#) of approximately 15°C up to 25 °C.

Before mixing, the A-component must be mechanically stirred, then the B-component is poured into the container of the A-component.

Make sure that the B component runs out completely, carefully scraping out the container with a spatula. Scrape the sides and the bottom of the pail several times with the mixer to ensure complete mixing.

Do not mix by hand, [mix](#) with a [mechanical](#) drill and paddle at a very low speed (ca. 300 rpm) for [2 - 3 minutes](#).

Keep the mixer blades submerged in the material to [avoid](#) introducing air [bubbles](#). Do not work out of the original drum / pail. After proper mixing to a homogeneous consistency pour the mixture into [a fresh pail](#) and [mix for another minute](#).

Consumption

The consumption of CONIFLOOR EP 112 N used as primer or a scratch coat is approximately between [0.4-0.8 kg/m²](#) [depending](#) on the condition and porosity of the substrate.

A [2nd coat of 0.4-0.6 kg/m² of primer](#) CONIFLOOR EP 112 N can be necessary [in](#) order to seal concrete pores and capillaries completely.

CONIFLOOR EP 112 N is also used in various parking deck coating systems. The corresponding minimum consumption values can be found in the corresponding system data sheets or test reports.

CONIFLOOR EP 112 N is used especially at unevenness of $\geq 0.5\text{mm}$.

In the case of highly absorbent substrates, it may be necessary to first prime with the unfilled primer CONIFLOOR EP 110 or EP 116 LE.

The above consumption figures are intended [as a guide only](#) and may increase on very rough or porous substrates. For filling CONIFLOOR EP 112 N as a scratch / levelling layer, fire-dried quartz sand with a grain size of 0.1-0.3 mm is recommended

CONIFLOOR EP 112 N should be applied when the ambient [temperature](#) is [constant](#) or falling as this will decrease the risk of bubble formation due to evaporation of air that is enclosed in the concrete.

CONIFLOOR EP 112 N is applied to the prepared substrate by a squeegee and if necessary finished with a roller. Puddles need to be avoided.

PUR Coatings

To ensure a good adhesion to a subsequently applied polyurethane or polyaspartic resin-based coating, we recommend [broadcasting the still fresh primer](#) layer CONIFLOOR EP 112 N with [fire-dried quartz sand](#) with a grain size of [0.3-0.8 mm](#) (consumption at least approx. 0.5-0.8 kg / m²). Avoid scattering in excess.

For [surfaces with low mechanical stress](#), a reworking with polyurethane or polyaspartic resins can be carried out without sanding [within the given reworking time](#), or the primer that [has not been broadcasted with quartz sand must be sanded well](#).

Temperatures

Both the processing time of CONIFLOOR EP 112 N and the hardening of the covering are largely determined by the temperature of the material, the substrate, and the environment. [At low temperatures, the chemical reactions are generally delayed; This also extends the pot, walk-on and recoat times](#). At the same time, the consumption per unit area may increase as a result of increasing viscosity. [Conversely, chemical reactions are accelerated at high temperatures, so that the above times are correspondingly shortened](#).

For CONIFLOOR EP 112 N to cure completely, the mean temperature of the substrate must not fall below the lowest processing or object temperature.

After application, the material should be protected from direct contact with water for approx. 24 h (at 20° C). Within this period, contact with water can cause a surface bloom and/or surface tackiness, both of which must be removed else the adhesion to the following coating is impaired.

Cleaning agent

Re-usable tools should be cleaned carefully with CLEANER 44 or e.g., isopropanol.

Substrate condition

The substrate (old and new) must be structurally sound, solid, free of loose particles and laitance, dust, oils, greases, rubber abrasion and other separating substances. The surface tensile strength of the surface to be primed must be at least 1.5 N/mm² (smallest individual value at least 1.0 N/mm²), the compressive strength at least 25 N/mm². The substrates must have reached their equilibrium moisture content and also be protected from the effects of rising water during use or special measures must be taken, such as applying an additional blocking primer (ask our technical service).

Concrete	max. 4 M-% moisture
Cement screed	max. 4 M-% moisture
with single layer application	

[2-fold, film-forming primer up to max. 6 M-% moisture](#) (we recommend consulting our technical sales or technical service)

With higher residual moisture up to max. 6 M-%, CONIFLOOR EP 112 N can be used as an [additional film-forming blocking primer](#). The first step is to be applied in a film-forming manner ([min. 600-700 g/m²](#)) and [not sanded](#). The [second work step](#) must take place within the revision times with a [minimum consumption rate of 300 g/m²](#).

The **temperature** of the substrate must be at least **3 °C** above the current dew point temperature.

There must be a regular DPM between the stone base and the slab.

Substrate preparation

The substrate must be prepared using suitable measures, such as shot blasting or diamond grinding, so that the requirements listed above are met. Fill broken areas and defects in the substrate with CONICA EP mortar flush with the surface.

The substrate to be coated must have an average adhesive tensile strength of at least 1.5 N / mm² (verification e.g., with Herion device, pulling speed 100 N / s).

The **residual moisture** in the substrate must not exceed **4 M-%**.

The consumption and the quantities given are guidelines and may be higher on very rough or porous surfaces. If necessary, exact consumption values can be determined on the object after the substrate has been pre-treated.

Pack size

CONIFLOOR EP 112 N is supplied in 25 kg working packs. A- and B-component are filled in separate cans in the suitable mixing ratio.

Color: beige

Storage

Store in original closed packing under dry conditions at a temperature range of 15 - 25 °C.

Do not expose the drums to direct sunlight.

Please check "best-before" date on the pail before usage.

Safety precautions

CONIFLOOR EP 112 N is non-hazardous in its cured condition.

For protective measures, transport regulations and waste management please refer to the Material Safety Data Sheet of the product.

VOC Contents

CONIFLOOR EP 112 N meets the requirements of the EC directive 2004/42/EC

The limit value for products ready for use (product type according to table IIA j Type sb) is:

Level II (from 2010) <500 g/l VOC.

When ready to use, this product contains less than 500 g/l VOC.



CE-Label / UKCA-Label:

See Declaration of Performance and CE and UKCA mark.

CONICA AG
Industriestrasse 26
8207 Schaffhausen
Suisse
Tel.: + 41 52 644 3600
Fax: + 41 52 644 3699
info@conica.com
www.conica.com

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the professional competence involved in the application of the product are beyond our control.

As all CONICA data sheets are updated on a regular basis, it is user's responsibility to obtain the most recent issue. Registered users can obtain the actual data sheets from our webpage. Hard copies are available upon request.