






	Caracteristici			
	Standard	Cerinte	Unitate	Rezultate
	<b>Descrierea Produsului</b>			
Tratament de suprafata	-	-	-	PUR PROTECT
Complex de suprafata	-	-	-	100% PVC
Spuma	-	-	-	Spumă cu celule închise
Grosime	EN 428	-	mm	<b>6 mm</b>
Greutate	EN 430	-	kg/m <sup>2</sup>	
Lungime	EN 426	-	ml	20.5 Standard
Latime	EN 426	-	ml	1,5
	<b>Proprietati Sportive</b>			
Absortia de soc	EN 14808	≥ 25	%	
Deformare verticala	EN 14809	≤ 3.5	mm	$P_1 \leq 3.5$
Energia intoarsa	NF P 90 203	≥ 0.31	m/s	≥ 0.31
Coeficientul de alunecare	EN 13036-4	80 to 110	-	80 - 110
Balans de minge	EN 12235	≥ 90	%	≥ 90
Ball speed	UEFA	50 to 65	cm	-
	ITF	-	-	-
	<b>Caracteristici Tehnice</b>			
Rezistenta la abraziune	EN ISO 5470-1	≤ 1000	mg	≤ 350
Rezistenta la impact	EN 1517	≥ 8	N/m	≥ 8
Rezistenta la indentare	EN 1516	≤ 0.5	mm	≤ 0.5
	<b>Clasificare</b>			
Comportament la foc	EN 13501-1	-	-	
	DOP n°xxx	-	-	Comportament la foc Absortie de soc Coeficient de alunecare Rezistenta la abraziune Rezistența la încărcare la rulare

	Metoda de instalare		
	Recomandari Gerflor	Unitate	Rezultate
Instalare cu adeziv: "Original"	Nivelul de umezeală a pardoselii	%	RH < 80% (BS 8203) or < 4.5% umiditate (CCM)
Instalare cu Isolsport: "Flexible"		%	RH < 80% (BS 8203) or < 7.0% umiditate (CCM)

COLOUR RANGE	
	Standard roll 20.5 lm