

Pellet ABS Kevlar

MATERIAL PROPERTIES

Density	1.05 g/cm ³	ISO 1183
Mechanical Properties		
Charpy impact strength		
Unnotched, injection moulding	14 kJ/m ²	ISO 179-1eU
Notched, injection moulding	6.1 kJ/m ²	ISO 179-1eA
Tensile Elongation at Yield *	1.9%	ISO 527 (1)
Tensile Elongation at Break *	6,00%	ISO 527 (1)
Tensile Strength at Yield *	35 MPa	ISO 527 (1)
Tensile Strength at Break *	30 MPa	ISO 527 (1)
Elastic modulus (speed 1 mm/min)	2350 MPa	ISO 527 (1)
Thermal Properties		
VICAT Softening point **	95°C	ISO 306
HDT 0.45 MN/m ² , annealed	88°C	ISO 75
HDT 1.81 MN/m ² , annealed	75°C	ISO 75

*speed 5mm/min

** 50 N (heating rate 50°C/h), injection moulding

GUIDELINE FOR PRINT SETTINGS*

Nozzle temperature	250-270°C
Bed temperature	100°C
Active cooling fan	0 - 25%
Closed chamber	not necessary
Dry box	not necessary
Ruby or hardened nozzle	recommended

* settings are based on a 0.4 mm nozzle.

DESCRIPTION


Spectrum Pellet ABS Kevlar is characterized by properties identical to the Spectrum ABS Kevlar filament - a material based on classic ABS enriched with aramid fibers. The material is characterized by higher strength and increased resistance as compared to standard ABS. The adjustments done ensure reduced processing shrinkage, very good adhesion to the working platforms and reduced density, resulting in slightly lighter prints than their counterparts manufactured using standard ABS.

FEAUTURES

- industrial-grade material
- material enriched with aramid fibres
- high rigidity and impact strength
- high mechanical strength
- very strong layer lamination

STORAGE AND SHELF LIFE

Filament should be stored in a dry room at room temperature. Recommended storage temperature is ca. 18-25°C (64.4 -77.0°F). Keep out of moisture, sunlight and direct heat. When stored properly, product has a shelf life of 24 months.



SUPPORT

If you have any questions or experience any issues, please do not hesitate to contact us at support@spectrumfilaments.com