



Cosmos Lac AE

1 Pindou str

17672 Kallithea, Athens - Greece

Phone.: +30 2109570222 -

Fax: +30 2109566671

factory@cosmoslac.com

www.cosmoslac.com

TECHNICAL DATA SHEET

PRODUCT IDENTIFIER	COSMOS LAC SPRAY PAINT HIGH HEAT
CODES	SILVER 350, BLACK 351, WHITE 352, RED OXIDE 353, BROWN 355, ANTHRACITE 356
SPECIFICATIONS	<p>Provides durable coating of surfaces that are heated to temperatures of +700°C.</p> <p>Recommended for metal surfaces that are exposed to very high temperatures. Applications include mufflers, exhaust systems, engine components, boilers, furnaces, ovens and oven inserts, chimneys, grills, electric and gas heaters, and incinerators.</p> <p>Contains only high quality Silicone resins.</p> <p>Matt finish.</p> <p>Fast drying.</p> <p>High Coverage.</p> <p>Rust resistant formulation.</p> <p>Not suitable for surfaces in direct contact with fire.</p>
APPLICATION	<p>Surface must be clean of rust, dust, dirt, grease, old paint etc. Apply at temperatures between +15°C and +30°C. Shake well for 2 minutes.</p> <p>Spray the surface at a distance of 20 – 30cm.</p>
DRYING	<p>Touch dry (1 layer, 20°C, Humidity<65%): 10'</p> <p>Through dry (1 layer, 20°C, Humidity<65%) : 1 hour</p> <p>Through dry (multiple layers): 24 hours</p>
CURING BY BAKING	<p>After applying the first layer, drying surface must be heated to 250°C for 30'.</p>
VOC CONTENT	V.O.C. density at 20 °C: 690 kg/m ³ (690 g/L)
Coverage	5m ² /L
Contents	400ml
After use	Spray holding the can inverted for 3". Clean the caps with solvent.
Storage	5-35°C. Do not put in vehicles.

ISSUED : 16 December 2017, factory@cosmoslac.com